Paraffin Wax HP3

Heavy grade paraffin wax. Slabs 25 x 50 x 4 cm.

Typical Properties (Guaranteed Limits)

Property	Specification	Test Method
Oil Content	**max 5.0 %wt**	ASTM D-721
Melting Point	**63 - 65 °C**	ASTM D-87
Colour	**min 18 Saybolt**	ASTM D-156
Penetration @ 25 °C	**max 23 (0.1 mm)**	ASTM D-1321
Kinematic Viscosity @ 100 °C	**6.5 - 8.0 cSt**	ASTM D-445

Typical Applications

High melting point applications: rubber and tire compounding (anti-ozonant wax blends), protective and anti-corrosion coatings, cable filling compounds, hot-melt formulations.

Packing

Slabs 25 x 50 x 4 cm packed in carton boxes, approx. 24 kg net per carton, stacked and loaded on pallets. Full truck load (FTL): 22 MT.

Storage & Handling

Store in a dry, ventilated area away from direct sunlight and heat sources. Keep cartons palletized; do not stack above supplier-marked limits.

Application suggestions are indicative; final suitability for a specific process or product is to be validated by the customer. This product is not certified for food, cosmetic or pharmaceutical use unless separately documented. The values above are guaranteed specification limits. A batch Certificate of Analysis with measured results accompanies every shipment. Independent pre-shipment inspection (e.g. SGS) is available on request. HS Code: 2712 20.