

Heavy Slack Wax H12

Heavy slack wax. Semi-refined petroleum wax for further processing and industrial use.

Typical Properties

Property	Specification	Test Method
Oil Content	10 - 16 %wt	ASTM D-721
Melting Point	min 57 °C	ASTM D-87
Kinematic Viscosity @ 100 °C	6 - 7.5 cSt	ASTM D-445
Colour	1.5 - 2.0	ASTM D-1500
Flash Point	min 200 °C	ASTM D-92

Typical Applications

Feedstock for wax de-oiling and refining, blending component, waterproofing agent for composite wood panels and canvas coatings, rubber processing, firelighters and firelogs, controlled release agent for chemicals and fertilizers.

Packing

1000 kg IBC or plastic tank, 1000 kg jumbo bag (FIBC), or 175 kg steel drums (new or reconditioned).

Storage & Handling

Store in tightly closed original containers in a dry, ventilated area away from direct sunlight and heat sources. Shelf life: 36 months from production date.

Application suggestions are indicative; final suitability for a specific process or product is to be validated by the customer. This product is not certified for food, cosmetic or pharmaceutical use unless separately documented. The values above are guaranteed specification limits. A batch Certificate of Analysis with measured results accompanies every shipment. Independent pre-shipment inspection (e.g. SGS) is available on request.