

Slack Wax HA25

Heavy slack wax, brownish. Semi-refined petroleum wax for further processing and industrial use.

Typical Properties

Property	Specification	Test Method
Oil Content	20.0 - 30.0 %wt	ASTM D-721
Melting Point	61 - 64 °C	ASTM D-127
Penetration @ 25 °C	40 - 80 (0.1 mm)	ASTM D-1321
Kinematic Viscosity @ 100 °C	5.0 - 7.0 cSt	ASTM D-445
Colour	Brownish	Visual
Flash Point	min 230 °C	ASTM D-92

Typical Applications

Feedstock for wax de-oiling and refining, wax emulsions for MDF / particleboard and chipboard, firelighters and firelogs, rubber processing and extender applications, dust suppression, controlled release agent for chemicals and fertilizers.

Packing

1000 kg IBC or jumbo bag (FIBC), or 175 kg steel drums.

Storage & Handling

Store in tightly closed original containers in a dry, ventilated area away from direct sunlight and heat sources. Shelf life: 36 months from production date.

Application suggestions are indicative; final suitability for a specific process or product is to be validated by the customer. This product is not certified for food, cosmetic or pharmaceutical use unless separately documented. The values above are guaranteed specification limits. A batch Certificate of Analysis with measured results accompanies every shipment. Independent pre-shipment inspection (e.g. SGS) is available on request.