

Medium Slack Wax MSW

Medium slack wax. Semi-refined petroleum wax for further processing and industrial use.

Typical Properties

Property	Specification	Test Method
Oil Content	max 31 %wt	ASTM D-721
Congealing Point	52 - 59 °C	ASTM D-938
Kinematic Viscosity @ 100 °C	4.5 - 6.5 cSt	ASTM D-445
Appearance	Yellow	Visual

Typical Applications

Feedstock for wax de-oiling and refining, blending component, waterproofing agent for composite wood panels and canvas coatings, candle manufacturing, controlled release agent for chemicals and fertilizers.

Packing

1000 kg jumbo bag (FIBC) or 1000 kg IBC.

Storage & Handling

Store in tightly closed original containers in a dry, ventilated area away from direct sunlight and heat sources. Shelf life: 36 months from production date.

Application suggestions are indicative; final suitability for a specific process or product is to be validated by the customer. This product is not certified for food, cosmetic or pharmaceutical use unless separately documented. The values above are guaranteed specification limits. A batch Certificate of Analysis with measured results accompanies every shipment. Independent pre-shipment inspection (e.g. SGS) is available on request.